

LFP Protec 303p

95μ Soft-PVC monomeric, transparent matt

Technical Product Information

Grade Characteristics

Description Self-adhesive monomeric soft-PVC, transparent matt, 95 microns

Application Overlaminating protection film with UV-absorbers to protect digital large format prints

Certificates

Recommended application temperature $min. + 10^{\circ}C$ Product application temperature $-30 \text{ to} + 80^{\circ}C$ Durability 3 years ^*

Shelf life at 23°C / 50% moisture 2 years in original boxes *

| Physical Properties Facestock | Value | Unit | Norm |
|---------------------------------|--------|--------|----------------|
| Caliper | 95 ± 5 | μm | ISO 534 |
| Stretch at break MD | > 160 | % | DIN EN ISO 527 |
| Tear resistance MD | > 26 | Мра | DIN EN ISO 527 |
| | | | |
| Physical Properties Adhesive | Value | Unit | Norm |
| Adhesion* P3 → Permanent, clear | 14 ±6 | N/25mm | Finat 1 |

*Average value 24h on Glass

Physical Properties Liner Caliper EN ISO

Caliper EN ISO 20 534 Substance ISO 536

K7W siliconised Glassinepaper 0,062mm 72g/m²

Guarantee

INTERCOAT materials are manufactured according to highest quality standards and pass stringent quality controls prior to despatch. Any material showing an evident defect of manufacturing will be replaced promptly without charge. The wide range of different applications does not allow to test all possibilities of employment. All statements, technical information and recommendations are based on tests and practical experiences and believed to be reliable but do not constitute a guarantee or warranty. Preliminary tests are recommended for each new application. For any need of advise or technical support the INTERCOAT technical department will be pleased to assist.

16.05.2014

Changes without notice

AMC AG Divison Intercoat Boschstr. 12 D-24568 Kaltenkirchen Telefon: +49-(0)4191-8005-0 Telefax: +49-(0)4191-2450 Internet: www.Intercoat.de



^{*} Normal storage and handling conditions. Middle-European climate conditions, unprinted.